DT15 Rec'd PCT/PTO 0 7 DEC 2004

20

CLAIMS

1. A method to obtain perfluorocarbonate polymers that contain fluorosulphonyl functional groups and that have structural formula (I):

5

AFT 34 PAC

(I)

10

that consists in copolymerization between tetrafluoroethylene and a perfluorovinylic ether in a fluorated organic solvent medium, in the presence of a radical type starter with additional input of tetrafluoroethylene during the copolymerization process, characterized because before starting the copolymerization, a previously synthesized dispersion is introduced of the copolymer of tetrafluoroethylene and perfluorovinylic ether, in an organic solvent.

15

Method according to claim 1 in which the previously synthesized dispersion
of the copolymer of tetrafluoroethylene and perfluorovinylic ether is
prepared in a perfluorated organic solvent in a proportion of 0.03 - 0.06%
of the liquid reagent mass.

20

Method according to claim 1 in which the previously synthesized dispersion
of copolymer of tetrafluoroethylene and perfluorovinylic ether in the organic
solvent presents a concentration of copolymer of between 10 and 20 % in
mass of this solvent.

25

4. Method according to the previous claims in which perfluorovinylic ether is perfluoride [4-methyl-3,6-dioxa-7-octene-1-fluorosulphonyl] (FC-141)

30

5. Method according to the previous claims in which the organic solvent is 1,1,2-trichloro-1,2,2-trifluoroethane (freon-113).

21

- 6. Method according to previous claims in which for a radical type starter perfluorate peroxide is used.
- 7. Method according to claim 6 in which perfluorocyclohexanoyl peroxide is used as perfluorate peroxide.
- 8. Method according to claim 7 in which the copolymerization is carried out at a temperature of 30-35°C and a pressure of 0.31-0 25 MPa.
- Method according to claim 6 in which perfluoropropionyl is used as fluorated peroxide.
 - 10. Method according to claim 9 in which the copolymerization process is carried out at a temperature of 70-80°C and a pressure of 9-14 MPa.

15

10

5